



# **A Review on Biodegradable Films from Banana Peel**

**Md Azizul Hakim Shiam<sup>a</sup>, Asraful Alam<sup>a\*</sup>,  
Mrityunjoy Biswas<sup>a\*</sup>, Mahfujul Alam<sup>a</sup>,  
Mohosina Hossain Misha<sup>a</sup>, Shahabuddin Ahmed<sup>b</sup>  
and Mustafa Kamrul Hasan<sup>a</sup>**

<sup>a</sup> Department of Agro Product Processing Technology, Jashore University of Science and Technology, Jashore-7408, Bangladesh.

<sup>b</sup> Department of Animal Nutrition, Khulna Agricultural University, Khulna-9202, Bangladesh.

## **Authors' contributions**

*This work was carried out in collaboration among all authors. All authors read and approved the final manuscript.*

## **Article Information**

DOI: <https://doi.org/10.9734/afsj/2024/v23i12756>

## **Open Peer Review History:**

This journal follows the Advanced Open Peer Review policy. Identity of the Reviewers, Editor(s) and additional Reviewers, peer review comments, different versions of the manuscript, comments of the editors, etc are available here: <https://www.sdiarticle5.com/review-history/126344>

**Review Article**

**Received: 13/09/2024**

**Accepted: 16/11/2024**

**Published: 25/11/2024**

## **ABSTRACT**

The increasing environmental issues associated with plastic waste have sparked a heightened interest in the creation of biodegradable alternatives derived from renewable resources. One notable option is biodegradable film made from banana peels, which presents an environmentally friendly and sustainable solution. This review examines the viability of utilizing banana peels as a raw material for the production of biodegradable films. It investigates the chemical makeup of banana peels, emphasizing the presence of starch, cellulose, and pectin, which are essential for film formation. The review further addresses various processing techniques, including starch extraction, plasticization, and cross-linking, that improve the mechanical properties and

\*Corresponding author: Email: [a.alam@just.edu.bd](mailto:a.alam@just.edu.bd), [mrityunjoy\\_appt@just.edu.bd](mailto:mrityunjoy_appt@just.edu.bd);

**Cite as:** Shiam, Md Azizul Hakim, Asraful Alam, Mrityunjoy Biswas, Mahfujul Alam, Mohosina Hossain Misha, Shahabuddin Ahmed, and Mustafa Kamrul Hasan. 2024. "A Review on Biodegradable Films from Banana Peel". *Asian Food Science Journal* 23 (12):33-46. <https://doi.org/10.9734/afsj/2024/v23i12756>.

biodegradability of the films. Moreover, it analyzes the environmental implications, potential applications in food packaging, and the challenges related to scalability and cost-effectiveness. The findings indicate that biodegradable films derived from banana peels represent a promising substitute for petroleum-based plastics; however, additional research is necessary to enhance their mechanical strength and commercial feasibility. The review concludes by advocating for ongoing investigation into natural waste resources for the development of sustainable materials.

*Keywords: Biodegradable film; banana peel; food waste; bio film; packaging.*

## 1. INTRODUCTION

In recent years, the growing environmental issues associated with the overuse of synthetic plastics have prompted significant research into sustainable alternatives. Biodegradable films have emerged as viable substitutes due to their natural degradation capabilities, which help mitigate pollution. Among the various organic materials being investigated, banana peels, a prevalent form of agricultural waste, have attracted considerable interest. Films derived from banana peels offer an eco-friendly solution by transforming organic waste into useful products, thereby reducing environmental impact while providing a range of mechanical and physical properties suitable for packaging and other industrial uses. The global dependence on plastic has led to a severe waste management crisis, particularly as synthetic plastics are non-biodegradable and can remain in the environment for centuries. It is estimated that approximately 8 million tons of plastic waste enter the oceans each year, with projections indicating that plastic pollution could quadruple by 2050 unless sustainable alternatives are implemented (Fu et al., 2021, Nanda et al., 2022, Pilapitiya et al., 2024, Evode et al., 2021, UNESCO).

The use of plastic packaging presents numerous detrimental effects on both the environment and public health. To begin with, the breakdown of plastic waste generates microplastics, which infiltrate ecosystems and threaten marine organisms as well as human health by entering the food chain (Kadac-Czapska et al., 2023). Furthermore, plastic packaging is a major contributor to greenhouse gas emissions throughout its entire life cycle, especially during the production and disposal phases (Irzalinda & Ardi, 2020). Additionally, plastic packaging often contains toxic substances that can leach into food, including endocrine disruptors and carcinogenic compounds, thereby posing significant health risks (Muncke, 2021). Finally,

despite ongoing recycling initiatives, the accumulation of plastic packaging waste continues due to inadequate recycling facilities and improper disposal methods, leading to enduring pollution (Groh et al., 2019).

Biodegradable plastics made from organic materials such as banana peels are emerging as a promising response to this pressing environmental challenge (Jangra et al., 2023, Shen et al., 2020). Banana peels are a rich source of natural biopolymers, including starch, cellulose, and pectin, making them particularly suitable for the creation of biodegradable films. These biopolymers can be processed into films that exhibit desirable mechanical and thermal properties. Research indicates that cellulose extracted from banana peels can significantly improve the tensile strength and thermal stability of biodegradable films, rendering them appropriate for packaging applications (Kumar et al., 2023). The successful development of films from banana peels not only addresses the issue of plastic waste but also provides an added value to agricultural by-products (Yusuf et al., 2016, Verma et al., 2024). The creation of films derived from banana peels employs a variety of methods, including the addition of fillers such as starch, citric acid, and plasticizers, which enhance the mechanical characteristics and biodegradability of the films (Verma et al., 2024, Chandrasekar et al., 2023). For instance, Jangra et al., (2023) illustrated that the combination of banana peel with industrial maize starch resulted in bioplastic films that decomposed within a week, offering a promising substitute for traditional plastics. These results are consistent with findings from other research, which emphasize the potential of banana peel powder as a reinforcing agent to improve the physical and chemical attributes of biodegradable films (Huzaisham, 2019). Additionally, investigations have concentrated on the characterization of banana peel-based films to assess their applicability in industrial settings. Research indicates that these films possess remarkable water vapor permeability, tensile

strength, and thermal stability, all of which are essential for food packaging materials (Ningtyas et al., 2021, Taweecat et al., 2021). Furthermore, the incorporation of plasticizers such as glycerol has been shown to enhance the flexibility of the films, facilitating their handling and making them more appropriate for packaging uses (Benitez et al., 2024, Rodríguez et al., 2006, Tarique et al., 2021).

Innovative approaches in this field have also included the integration of banana peel biopolymers with other substances, such as cellulose nanofibers and bacterial cellulose. These combinations have demonstrated a significant improvement in the mechanical and barrier properties of the films, rendering them more robust and resistant to environmental challenges (Borela & Apolinar, 2020, Muhammad et al., 2020). Such developments highlight the potential of banana peel films as a sustainable alternative to petroleum-based plastics within the packaging sector. The development of biodegradable films derived from banana peels has shown considerable promise; however, several challenges persist. A primary concern is ensuring that these films satisfy the stringent requirements for industrial applications, particularly regarding mechanical strength, thermal stability, and biodegradability. Recent research has suggested the need for additional studies focused on optimizing processing conditions and formulations to improve the characteristics of these films (Ng et al., 2021). For example, incorporating citric acid has been found to enhance the tensile strength and durability of banana peel-based films, potentially addressing some of the existing challenges (Hardjono et al., 2016; Oliveira et al., 2017). Biodegradable films produced from banana peels signify a notable progress in sustainable material development. These films offer a viable alternative to conventional plastics and contribute to the recycling of agricultural waste. Although further research is required to improve their properties for commercial use, current studies indicate that films made from banana peels could transform the packaging sector by offering an eco-friendly solution to the issues associated with plastic waste.

## 2. COMPOSITION OF BANANA PEEL

The composition of banana peel is characterized by a diverse array of bioactive compounds, nutrients, and fibers, which enhance its potential uses across various sectors, including food,

agriculture, and pharmaceuticals. Notably, banana peels are abundant in dietary fibers, which constitute approximately 40-50% of their total content. These fibers comprise cellulose, hemicelluloses, and lignin, with notable differences influenced by the banana variety and its ripeness. The substantial fiber content is beneficial for promoting digestive health and reducing cholesterol levels (Emaga et al., 2007, Hassan et al., 2018). Green banana peels are particularly high in resistant starch, containing around 22.6% starch. As the banana matures, this starch undergoes conversion into sugars through enzymatic processes (Li et al., 2018, Cordenunsi-Lysenko et al., 2019). Over 40 unique phenolic compounds, encompassing flavonoids and tannins, have been identified in banana peels. These compounds are recognized for their potent antioxidant and antimicrobial properties, which are associated with a range of health benefits. Significant concentrations of notable polyphenols, including catechin, gallic acid, and quercetin, have also been observed (Vu et al., 2018, Rebello et al., 2014). Furthermore, banana peels contain 8-11% protein, with essential amino acids like leucine, valine, phenylalanine, and threonine present in considerable amounts. Lysine is identified as a limiting amino acid in banana peels (Emaga et al., 2007). The lipid content in these peels ranges from 0.90% to 10.44%, with a predominance of polyunsaturated fatty acids, particularly linoleic acid and  $\alpha$ -linolenic acid. These fatty acids enhance the nutritional profile of the peels and suggest their potential applications in skincare and therapeutic fields (Aboul-Enein et al., 2016, Oliveira et al., 2008). Additionally, banana peels are abundant in essential minerals, with potassium being the most prevalent, followed by calcium, magnesium, and phosphorus. These minerals play vital roles in various physiological functions, including muscle contraction and maintaining bone health (Aboul-Enein et al., 2016). Furthermore, banana peels contain approximately 15.89-24.08% pectin, which can be extracted for use as a gelling agent in food products such as jams. The quality of pectin derived from banana peels positions them as a valuable resource for industrial applications (Khamsucharit et al., 2017). According to another study, the yield of pectin produced was 17.19% (Tugon et al., 2023). They also contain carotenoids, including lutein,  $\beta$ -carotene, and  $\alpha$ -carotene, which not only contribute to the peel's coloration but also offer health benefits, such as supporting eye health and providing antioxidant properties (Subagio et al., 1996). Overall,

**Table 1. Nutritional component of banana peel**

Category	Nutritional Component	Range of Average Content (% DM)
<b>Carbohydrates</b>	Carbohydrate	59.51 – 76.58
	Starch	3.5 – 6.3
	Resistant Starch	2.3 – 2.5
<b>Fibers</b>	Dietary Fibre	47 – 53
<b>Proteins &amp; Fats</b>	Crude Protein	5.5 – 7.87
	Crude Fat	2.24 – 11.6
<b>Minerals</b>	Ash	9 – 11

banana peels are a rich source of bioactive compounds, fibers, minerals, and other nutrients, making them suitable for a wide range of applications, from dietary supplements to industrial uses.

According to several studies, nutritional component of banana peel is given in the following Table 1: (Essien et al. 2005, Lee, Yeom, Ha, & Bae, 2010, Emaga et al. 2007).

Due to its abundant nutritional profile, banana peels have a wide range of applications. An article by Zaini et al. (2022) highlights the multifaceted benefits of banana peels, emphasizing their nutritional components, which include various chemical compounds, fatty acids, amino acids, and dietary fiber. The article also points out their pharmacological advantages, such as antioxidant, antimicrobial, and anticancer effects. Furthermore, the peel contains anti-nutrients, including phytate, alkaloids, oxalate, and glycosides. Ultimately, banana peels serve diverse roles in the food industry, being utilized in food ingredients, products, and packaging, thereby establishing them as a significant resource in both nutrition and industry.

### 3. DEVELOPMENT OF BIODEGRADABLE FILM BASED ON BANANA PEEL

The creation of biodegradable films from banana peels represents an effective method for repurposing food processing byproducts (Verma et al., 2024). Among agricultural residues, banana peels remain underutilized. The starch extracted from banana peels can be transformed into biofilm. Given its high amylopectin content, an acid modification process utilizing HCl solution was employed to convert amylopectin into amylose or smaller starch fragments. This modification results in a biofilm characterized by a denser matrix, thereby enhancing the material's tensile strength. Glycerol was incorporated as a low molecular weight plasticizer to increase the free volume of the polymer matrix, facilitating the movement of

polymer chains, which subsequently enhances the elongation at break of the biofilm. Films derived from banana peels address a significant challenge in the industry by improving efficiency and simultaneously contributing to the economy through various applications where plastic wrapping is traditionally utilized. These banana-based films can serve as packaging for dried foods, quick-dissolving ingredients, or as wraps and coatings for food products, thereby providing nutritional benefits and convenience while minimizing food packaging waste (Nimbolkar et al., 2023).

Banana peel fiber has the potential to contribute to the creation and advancement of biodegradable films, providing an eco-friendly alternative to mitigate the harmful impacts of plastic materials. These films exhibit transparency and demonstrate a tensile strength of 31.3 MPa, with thickness measurements varying between 0.057 mm and 0.090 mm (Hoque et al., 2024).

The addition of nanofibers, such as cellulose nanocrystals (CNCs), or chemical additives like citric acid, has been found to further enhance the properties of these films. Citric acid functions as a crosslinking agent, creating stronger hydrogen bonds that improve mechanical stability and water resistance (Oliveira et al., 2017). Various types of biodegradable films from banana peel can be categorized as follows:

#### 3.1 Starch-Based Biodegradable Films

Banana peels, which are abundant in starch, serve as a crucial component in the formulation of biodegradable films. These starch-based films exhibit improved tensile strength and barrier properties, making them ideal for food packaging applications. Numerous studies have focused on optimizing these formulations by incorporating additives such as glycerol to enhance flexibility and citric acid to mitigate browning and bolster film stability (Jangra et al., 2023, Chandrasekar et al., 2023).




Fig. 1. Biodegradable packaging films from banana peel fiber (Hoque et al., 2024)

### 3.2 Nanocomposites

The integration of cellulose nanocrystals (CNCs) and other nanomaterials represents a significant advancement in film technology. CNCs contribute to enhanced tensile strength, thermal stability, and water resistance, positioning these films as promising alternatives to traditional packaging materials (Zhang et al., 2024, Newase & Bankar, 2017).

### 3.3 Pectin-Based Films

Films derived from pectin extracted from banana peels, in conjunction with various natural additives, create robust crosslinked networks. These films display excellent

barrier and mechanical characteristics, particularly when crosslinking agents such as citric acid are incorporated (Chodijah et al., 2019).

### 3.4 Hybrid Films

The integration of banana peel starch with other biopolymers, including corn starch or protein isolates, has shown improved biodegradability and strength. For instance, the combination of banana peel with polyvinyl alcohol (PVA) or soy protein has produced resilient, flexible, and environmentally friendly films that are well-suited for packaging and agricultural uses (Agustin & Padmawijaya, 2017, Balavairavan & Saravanakumar, 2021).




Fig. 2. Application of Banana Peel to Food Packaging (Salazar et al., 2021; Zhang et al., 2019; Silva et al., 2020, Santhoskumar et al., 2019, Hardjono et al., 2016, Hoque et al., 2024, Borela & Apolinar, 2020)

**Table 2. Biodegradable films from banana peel**

Type	Formulation of Film Forming Solution	Film Preparation Method	Film Physical Properties	Film Functional Properties	References
Starch-based	Banana peel starch, glycerol, citric acid	Solvent casting	Thickness: 0.387 mm, tensile strength: 10.56 MPa	Water resistance: 63.63%, biodegradable within 1 week	(Chodijah et al., 2019)
Nanocomposite	Banana peel pectin, cellulose nanocrystals (CNCs), citric acid	Solvent casting	Tensile strength: 7.92 MPa, elongation at break: 4.26%	High barrier to water vapor, strong hydrogen bonding	(Oliveira et al., 2017)
Starch-based	Banana peel, corn starch, glycerol, acetic acid	Solvent casting	Tensile strength: 3.50 N, water absorption: 50%	Biodegradable within 7 days	(Jangra et al., 2023)
PVA-based	Polyvinyl alcohol (PVA), banana peel filler, glycerol	Solvent casting	Tensile strength: 44.5 MPa, Young's modulus: 66.7 GPa	Water absorption: 42.3%, thermally stable up to 300°C	(Balavairavan & Saravanakumar, 2021)
Hybrid biopolymer	Banana peel starch, egg shell, epoxy resin	Casting	Thickness: 0.1-0.15 mm	Bio-degradable, surface roughness supports bio-interaction	(Yusuf et al., 2016)
Protein-based	Soy protein isolate, banana peel cellulose nanofibers	Solution casting	Tensile strength: 1250-1666.67 N/m <sup>2</sup>	Biodegradable	(Borela & Apolinar, 2020)
Pectin-based	Pectin from banana peel, CMC, glycerol, tapioca flour	Solvent casting	Tensile strength: 8.22 MPa, Young's modulus: 0.20347 MPa, Thickness: 1.025 mm, Elongation percentage is 40.4%	Biodegradable,	(Ningtyas et al., 2021)
Banana Peel/ Corn Starch Blend	Banana peel, corn starch, glycerol, acetic acid	Solvent casting	Tensile strength: 34.72 N/m <sup>2</sup> , water absorption: 60.65%	High thermal stability, biodegradable	(Sultan & Johari et al., 2017)
Cellulose/Banana Peel Composite	Cellulose, banana peel powder, plasticizer	Regeneration method	Uniform filler distribution, Tensile strength: 74.16 Mpa, Elongation percentage is 6.85%	Improved thermal stability, suitable for food packaging	(Rajini et al. 2021)
Banana Peel starch based	Banana peel starch, citric acid, glycerol	Casting	Tensile strength: 4.202 MPa (with CaCO <sub>3</sub> ), improved flexibility	Biodegradable, stronger with crosslinking agents	(Hardjono et al., 2016)

Type	Formulation of Film Forming Solution	Film Preparation Method	Film Physical Properties	Film Functional Properties	References
Banana Starch Composite film	Banana peel starch, eggshell, orange waste, glycerol	Solvent casting	Thickness: 0.07 mm, Porous structure, water solubility: 20.10%, high adsorption capacity	Used as biosorbent for heavy metal removal, water barrier properties, improved adsorption capacity	(Vonnie et al., 2023)
Banana Peel Edible Film	Banana peel, acetic acid, glycerol, plasticizer	Solvent casting	Thickness: 0.90 mm, tensile strength: 1.83 kg/cm <sup>2</sup> , Elongation at break: 93.73 %, Water solubility 70.11 %	Transparent, flexible, water-soluble	(Tak & Jain et al., 2019)
Banana Peel and Polyvinyl Alcohol (PVA)	PVA, banana peel waste, glycerol	Solution casting	Tensile strength: 32.52–46.97 MPa	High biodegradability, suitable for daily uses	(Ng et al., 2021)
Banana Peel and <i>Eriobotrya Japonica</i> Film	Banana peel flour, starch, <i>Eriobotrya japonica</i> extract	Solvent casting	Tensile strength reduced with extract addition	Antioxidant properties, good elongation	(Silva et al., 2020)
Biodegradable Planting Bag	Banana peel extract, thermoplastic starch	Solvent casting	Tear resistance: 66.388 N/mm	Rapid biodegradation in soil	(Huzaisham & Marsi et al., 2020)
Banana Peel Starch	Banana peel starch, plasticizer	Solvent casting	Degraded at rapid rate	Rapid degradation, viable alternative to plastics	(J et al., 2023)

Banana peel-derived edible films, infused with spices such as cumin, oregano, garlic, and pepper, were utilized as wraps for grilled chicken. This film enhanced the chicken's shelf life by minimizing microbial proliferation and creating a barrier against oxidation during refrigerated storage (Salazar et al., 2021). Additionally, a composite film formulated from chitosan and banana peel extract served as a coating to maintain the quality of apples during storage. This film demonstrated antioxidant properties, which contributed to preserving freshness and preventing oxidative damage (Zhang et al., 2019). Films produced from banana peel cellulose nanofibers were developed for biodegradable food packaging. These films displayed improved mechanical strength and biodegradability, making them appropriate for various food packaging needs (Borela & Apolinar, 2020). A study's findings indicate that banana film may serve as an appropriate edible packaging solution for dried foods, instant water-soluble ingredients, or as a wrap or coating for food products. This innovation could enhance nutritional value and convenience for consumers while simultaneously minimizing food packaging waste (Santhoskumar et al., 2019). Furthermore, banana peel and starch films enhanced with extracts from *Eriobotrya japonica* leaves, might be applied to the coating of perishable foods aiming to increase shelf-life minimizing spoilage, and providing antioxidant protection (Silva et al., 2020). These examples highlight the adaptability of banana peel-based biodegradable films in food preservation and packaging, presenting sustainable and environmentally friendly alternatives to traditional plastics.

#### **4. BENEFITS OF USING BANANA PEEL BASED COMPONENTS IN PACKAGING DEVELOPMENT**

Banana peel-derived materials have been investigated for their potential advantages in the development of packaging solutions (Zhang et al., 2020). As a plentiful agricultural byproduct, banana peel can be transformed into biodegradable packaging options, thereby diminishing dependence on conventional plastics and mitigating environmental pollution (Arjun et al., 2023). Films produced from banana peel composites are characterized by their lightweight and robust nature, positioning them as a feasible substitute for high-density polyethylene (HDPE) and polystyrene plastics (Koo et al., 2022). Bioplastics produced from banana peels

demonstrate commendable mechanical strength and thermal stability; however, their performance may not consistently surpass that of all synthetic plastics across all parameters, especially in high-performance applications that demand exceptional durability (Azieyanti et al., 2020). For instance, composites of cellulose and banana peel powder reveal superior tensile and thermal characteristics, rendering them appropriate for packaging uses (Erna et al., 2023). The addition of banana peel extracts to films boosts their antioxidant and antimicrobial properties, thereby prolonging the shelf life of food items. These films can serve as active packaging solutions, such as chitosan films enriched with banana peel extracts, which have shown effectiveness in maintaining the postharvest quality of fruits (Zhang et al., 2019). The application of banana peels in packaging not only minimizes waste but also offers an economical alternative to traditional materials. Research indicates that banana peel biocomposites are cost-effective and straightforward to manufacture, providing a sustainable option for industries in search of budget-friendly packaging solutions (Sakr et al., 2024).

#### **5. CONCLUSION**

Recent developments in the creation of biodegradable films from banana peels demonstrate their potential as an environmentally friendly substitute for synthetic plastics. These films possess remarkable biodegradability and favorable mechanical characteristics, making them ideal for uses in packaging and agriculture. They are capable of breaking down naturally within a matter of weeks, thus offering a practical method to mitigate plastic waste. Enhancing specific properties such as tensile strength and water vapor permeability may allow for expanded industrial applications. Bioplastics diminish dependence on fossil fuels and enhance the carbon footprint, contributing to environmental conservation and resource efficiency, particularly within the packaging sector. Additionally, they provide advantages in agriculture by breaking down to stabilize root temperatures, preserve soil nutrients and moisture, and promote plant development. The manufacture of these films represents a significant opportunity to decrease ecological impact by repurposing agricultural by products (Jangra et al., 2023; Chodijah et al., 2019; Pelissari et al., 2013; Ningtyas et al., 2021; Devika & Saha, 2024).



## 6. LIMITATION OF USING BANANA PEEL BASED BIOPLASTIC

Banana peel-based bioplastics offer a promising environmentally friendly alternative to petroleum-based plastics, showcasing superior tensile strength, Young's modulus, and resistance to various testing parameters (A. et al., 2024; Vimal et al., 2024). However, there are limitations to consider when comparing them to petroleum-based plastics. While banana peel bioplastics exhibit biodegradability and some chemical resistance similar to traditional plastics (Fatima et al., 2023), they may have lower water absorption and elongation properties (A. et al., 2024). Additionally, the mechanical properties of banana peel bioplastics can be enhanced by adding chitosan and glycerol (Erna et al., 2023). Despite these enhancements, banana peel-based bioplastics may still face challenges in achieving the same level of mechanical strength and versatility as petroleum-based plastics, which have been widely used in various industries for their durability and flexibility (Azieyanti et al., 2020; Izzah et al., 2024).

## 7. FUTURE PERSPECTIVES

The future outlook for biodegradable films made from banana peels is highly encouraging, with numerous advancements anticipated to enhance their functionality and effectiveness in packaging applications. Upcoming research will aim to strengthen the mechanical characteristics of banana peel films by fine-tuning the concentration of reinforcing agents, such as cellulose nanofibers, to ensure these films can achieve comparable strength and durability to synthetic plastics (Borela & Apolinar, 2020). Additionally, further innovations are expected to improve the water resistance and barrier properties of banana peel films through chemical modifications, thereby increasing their suitability for food packaging purposes (Oliveira et al., 2017). However, the scalability of banana peel films for industrial production presents a significant challenge. Future initiatives will concentrate on creating cost-effective and energy-efficient methods for large-scale manufacturing (Jangra et al., 2023). Scientists are likely to explore using banana peel films as a packaging material by adding antimicrobial agents to them, which could potentially extend the shelf life of perishable foods by actively inhibiting the growth of bacteria on the food surface, creating a more effective active

packaging solution (Nunes et al., 2023; Taweechat et al., 2021). In summary, with advancements in mechanical, barrier, and functional properties, banana peel films represent a significant sustainable alternative to conventional synthetic plastics.

## DISCLAIMER (ARTIFICIAL INTELLIGENCE)

We hereby declare that NO generative AI technologies such as Large Language Models (ChatGPT, COPILOT, etc.) and text-to-image generators have been used during the writing or editing of this manuscript.

## COMPETING INTERESTS

Authors have declared that no competing interests exist.

## REFERENCES

- A., R., Norafifah, Izzati., A., M., Hanis, Madihah., N., Mohd, Nurazzi., M.K., Mohamad, Haafiz. (2024). The Effect of Cellulose Loadings on the Properties of Tapioca/Banana Peels Starch Bioplastics. <http://doi.org/10.21203/rs.3.rs-4210538/v1>
- Aboul-Enein, A., Salama, Z., Gaafar, A., Aly, H., bou-Elella, F., & Ahmed, H. (2016). Identification of phenolic compounds from banana peel (*Musa paradaisica L.*) as antioxidant and antimicrobial agents. *Journal of Chemical and Pharmaceutical Research*, 8.
- Agustin, Y. E., & Padmawijaya, K. S. (2017, July). Effect of glycerol and zinc oxide addition on antibacterial activity of biodegradable bioplastics from chitosan-kepok banana peel starch. *In IOP Conference Series: Materials Science and Engineering* (Vol. 223, No. 1, p. 012046). IOP Publishing. <https://doi.org/10.1088/1757-899X/223/1/012046>
- Arjun, J., Manju, R., Rajeswaran, S. R., & Chandhru, M. (2023). Banana peel starch to biodegradable alternative products for commercial plastics. *GSC Biological and Pharmaceutical Sciences*, 22(2), 234-244.
- Azieyanti, N. A., Amirul, A., Othman, S. Z., & Misran, H. (2020, April). Mechanical and morphology studies of bioplastic-based banana peels. *In Journal of Physics*:

- Conference Series (Vol. 1529, No. 3, p. 032091). IOP Publishing.
- Balavairavan, B., & Saravanakumar, S. (2021). Characterization of Ecofriendly Poly (Vinyl Alcohol) and Green Banana Peel Filler (GBPF) Reinforced Bio-Films. *Journal of Polymers and the Environment*, 29, 2756 - 2771. <https://doi.org/10.1007/s10924-021-02056-y>.
- Benitez, J. J., Florido-Moreno, P., Porrás-Vázquez, J. M., Tedeschi, G., Athanassiou, A., Heredia-Guerrero, J. A., & Guzman-Puyol, S. (2024). Transparent, plasticized cellulose-glycerol bioplastics for food packaging applications. *International Journal of Biological Macromolecules*, 132956. <https://doi.org/10.1016/j.ijbiomac.2024.132956>
- Borela, V., & Apolar, D. (2020). Banana Peel Cellulose Nanofibers (CNFs) as Retrofitting Material to Soy-Protein in Manufacturing Biodegradable Food Packaging. *Journal of Scientific Research in Medical and Biological Sciences*. <https://doi.org/10.47631/jsrmb.v1i1.22>.
- Chandrasekar, C. M., Krishnamachari, H., Farris, S., & Romano, D. (2023). Development and characterization of starch-based bioactive thermoplastic packaging films derived from banana peels. *Carbohydrate Polymer Technologies and Applications*, 5, 100328. <https://doi.org/10.1016/j.carpta.2023.100328>
- Chodijah, S., Husaini, A., Zaman, M., & Hidayat, H. (2019). Extraction of Pectin from Banana Peels (*Musa paradisiaca forma typica*) for Biodegradable Plastic Films. *Journal of Physics: Conference Series*, 1167,1-8. <https://doi.org/10.1088/1742-6596/1167/1/012061>.
- Cordenunsi-Lysenko, B. R., Nascimento, J. R. O., Castro-Alves, V. C., Purgatto, E., Fabi, J. P., & Peroni-Okyta, F. H. G. (2019). The starch is (not) just another brick in the wall: the primary metabolism of sugars during banana ripening. *Frontiers in Plant Science*, 10, 391. <https://doi.org/10.3389/fpls.2019.00391>
- Emaga, T., Andrianaivo, R., Wathélet, B., Tchango, J., & Paquot, M. (2007). Effects of the stage of maturation and varieties on the chemical composition of banana and plantain peels. *Food Chemistry*, 103, 590-600. <https://doi.org/10.1016/J.FOODCHEM.2006.09.006>.
- Erna, Rusliana, Muhamad, Saleh., Sri, Utami. (2023). Characteristics of biodegradable plastic from mulu bebe banana peel starch with the addition of chitosan and glycerol plasticizer. *IOP Conference Series*, 1177(1):012047-012047. <http://doi.org/10.1088/1755-315/1177/1/012047>
- Essien, J., Akpan, E., & Essien, E. (2005). Studies on mould growth and biomass production using waste banana peel. *Bioresource Technology*, 96 13, 1451-6 . <https://doi.org/10.1016/J.BIORTECH.2004.12.004>.
- Evode, N., Qamar, S. A., Bilal, M., Barceló, D., & Iqbal, H. M. (2021). Plastic waste and its management strategies for environmental sustainability. *Case Studies in Chemical and Environmental Engineering*, 4, 100142. <https://doi.org/10.1016/j.csee.2021.100142>
- Fatima Haliru Wali, Hannatu Sani Abubakar, Abubakar Umar Birnin-Yauri, Sayudi Yahaya Haruna. (2023). Development and characterization of starch based bioplastics using banana peels. *American Journal of Polymer Science and Technology*, 9(2), 21-25. <https://doi.org/10.11648/j.ajpst.20230902.12>
- Fu, B., Mei, S., Su, X., Chen, H., Zhu, J., Zheng, Z., Lin, H., Dai, C., Luque, R., & Yang, D. (2021). Integrating waste fish scale-derived gelatin and chitosan into edible nanocomposite film for perishable fruits. *International Journal of Biological Macromolecules*. <https://doi.org/10.1016/j.ijbiomac.2021.09.171>.
- Hardjono, H., Suharti, P., Permatasari, D., & Sari, V. (2016). Pengaruh penambahan asam sitrat terhadap karakteristik film plastik biodegradable dari pati kulit pisang kepok (*Musa acuminata balbisiana Colla*). , 5,22-28. <https://doi.org/10.15294/JBAT.V5I1.5965>.
- Hassan, U., Hassan, H., Ushie, O., Ibrahim, A., & Tabe, N. (2018). Exploring the Potentials of Banana (*Musa sapientum*) Peels in Feed Formulation. *International Journal of Advanced Research in Chemical Science*, 5, 10-14. <https://doi.org/10.20431/2349-0403.0505003>.
- Hoque, M., & Janaswamy, S. (2024). Biodegradable packaging films from banana peel fiber. *Sustainable Chemistry and Pharmacy*, 37, 101400.

- Huzaisham, N. (2019). Application of waste banana peels as biodegradable plastic. *Science Proceedings Series*. <https://doi.org/10.31580/SPS.V112.786>.
- Huzaisham, N. A., & Marsi, N. (2020). Utilization of banana (*Musa paradisiaca*) peel as bioplastic for planting bag application. *International Journal of Advanced Research in Engineering and Technology (IJARET)*, 11(4).
- Izzah, Aqilah, Arifin., Noraini, Marsi., Anika, Zafiah, Mohd, Rus., Ilyia, Izzati, Jamal., Asmadi, Md, Said. (2024). Biodegradable, Physical and Mechanical Characteristics of Banana Peel (*Musa paradisiaca*) for Bioplastics Polymer Composites. *Journal of Advanced Research in Applied Mechanics*, <http://doi.org/10.37934/aram.115.1.117>
- J, A., R., M., R, R., & M, C. (2023). Banana peel starch to biodegradable alternative products for commercial plastics. *GSC Biological and Pharmaceutical Sciences*. <https://doi.org/10.30574/gscbps.2023.22.2.0066>.
- Jangra, M., Deepika, D., Nehra, K., Dhankhar, K., Rani, S., Rani, P., Sharma, A., Sanju, S., & Ritu, R. (2023). Utilisation of Waste Banana Peels for the Preparation of Environment Friendly Bio-plastic Film: A Preliminary Study. *Shodh Sari-An International Multidisciplinary Journal*. <https://doi.org/10.59231/sari7608>.
- Koo, K., Zhong, A., Song, K., Choi, A., Feng, M., Yilmaz, A., Noh, V., Lee, N., & Lee, J. (2022). Developing a biodegradable packaging material using banana peel-based plastic. *Journal of Basic and Applied Research International*. <https://doi.org/10.56557/jobari/2022/v28i57925>.
- Kumar, V., Chakraborty, P., Janghu, P., Umesh, M., Sarojini, S., Pasrija, R., ... & Sivalingam, A. M. (2023). Potential of banana based cellulose materials for advanced applications: A review on properties and technical challenges. *Carbohydrate Polymer Technologies and Applications*, 100366. <https://doi.org/10.1016/j.carpta.2023.100366>
- Lee, E., Yeom, H., Ha, M., & Bae, D. (2010). Development of banana peel jelly and its antioxidant and textural properties. *Food Science and Biotechnology*, 19, 449-455. <https://doi.org/10.1007/S10068-010-0063-5>.
- Li, Z., Guo, K., Lin, L., He, W., Zhang, L., & Wei, C. (2018). Comparison of Physicochemical Properties of Starches from Flesh and Peel of Green Banana Fruit. *Molecules: A Journal of Synthetic Chemistry and Natural Product Chemistry*, 23. <https://doi.org/10.3390/molecules23092312>.
- Ningtyas, R. M., Nugroho, H., & Sabrina, A. (2021). Mechanical properties of edible film from Tanduk banana (*Musa corniculata Rumph*) peels for food packaging. *IOP Conference Series: Materials Science and Engineering*, 1011, 1-8. <https://doi.org/10.1088/1757-899X/1011/1/012060>.
- Muhammad, Naeem., Qasim, Siddiqui., Muhammad, Mushtaq., Amjad, Farooq., Zengyuan, Pang., Qufu, Wei. (2020). Insitu Self-Assembly of Bacterial Cellulose on Banana Fibers Extracted from Peels. *Journal of Natural Fibers*, 17(9):1317-1328. <http://doi.org/10.1080/15440478.2018.1563580>
- N., , R., , O., , K., , G., M., S., & , F. (2017). Banana (*Musa sp.*) peels as a source of pectin and some food. <https://doi.org/10.21608/jsas.2016.3028>.
- Nanda, S., Patra, B. R., Patel, R., Bakos, J., & Dalai, A. K. (2022). Innovations in applications and prospects of bioplastics and biopolymers: a review. *Environmental Chemistry Letters*, 20(1), 379–395. <https://doi.org/10.1007/s10311-021-01334-4>
- Newase, S., & Bankar, A. V. (2017). Synthesis of bio-inspired Ag–Au nanocomposite and its anti-biofilm efficacy. *Bulletin of Materials Science*, 40, 157-162.
- Ng, Q., Kalaiarasi, V., Teoh, Y., Ooi, Z., Shuit, S., & Low, C. (2021). Effect of banana peel waste concentration and mixing rate to the tensile strength of polyvinyl alcohol/banana peel waste composite film: optimization study via statistical tool. *IOP Conference Series: Earth and Environmental Science*, 765. <https://doi.org/10.1088/1755-1315/765/1/012031>.
- Yusuf, N., Rosly, E., Mohamed, M., Bakar, B., Yusoff, M., Sulaiman, M., & Ahmad, M. (2016). Waste Banana Peel and its Potentialization in Agricultural Applications: Morphology Overview. *Materials Science Forum*, 840, 394-398. <https://doi.org/10.4028/www.scientific.net/MSF.840.394>.
- Nimbolkar, P. K., Dhar, S., Kashyap, S. and Talukdar, N. 2023. Production of

- Biodegradable Plastic Film Using Banana Peel. *Vigyan Varta* 4(12): 288-291.
- Nunes, C., Silva, M., Farinha, D., Sales, H., Pontes, R., & Nunes, J. (2023). Edible Coatings and Future Trends in Active Food Packaging-Fruits' and Traditional Sausages' Shelf Life Increasing. *Foods* (Basel, Switzerland), 12(17),3308.<https://doi.org/10.3390/foods12173308>
- Oliveira, L., Freire, C., Silvestre, A., & Cordeiro, N. (2008). Lipophilic extracts from banana fruit residues: a source of valuable phytosterols. *Journal of agricultural and food chemistry*, 56 20, 9520-4. <https://doi.org/10.1021/jf801709t>.
- Oliveira, T., Rosa, M., Ridout, M., Cross, K., Brito, E., Silva, L., Mazzetto, S., Waldron, K., & Azeredo, H. (2017). Bionanocomposite films based on polysaccharides from banana peels. *International journal of biological macromolecules*, 101, 1-8 . <https://doi.org/10.1016/j.ijbiomac.2017.03.068>.
- Pelissari, F., Andrade-Mahecha, M., Sobral, P., & Menegalli, F. (2013). Comparative study on the properties of flour and starch films of plantain bananas (*Musa paradisiaca*). *Food Hydrocolloids*, 30, 681-690. <https://doi.org/10.1016/J.FOODHYD.2012.08.007>.
- Pilapitiya, P. N. T., & Ratnayake, A. S. (2024). The world of plastic waste: A review. *Cleaner Materials*, 100220. <https://doi.org/10.1016/j.clema.2024.100220>
- Rebello, L., Ramos, A., Pertuzatti, P., Barcia, M., Castillo-Muñoz, N., & Hermosín-Gutiérrez, I. (2014). Flour of banana (*Musa AAA*) peel as a source of antioxidant phenolic compounds. *Food Research International*, 55, 397-403. <https://doi.org/10.1016/J.FOODRES.2013.11.039>.
- Rodríguez, M., Osés, J., Ziani, K., & Maté, J. I. (2006). Combined effect of plasticizers and surfactants on the physical properties of starch based edible films. *Food Research International*, 39(8), 840-846. <https://doi.org/10.1016/j.foodres.2006.04.002>
- Sakr, S. (2024). Banana Peel Utilization: Practice and Perspective, Highlights from Lebanon. *International Journal of Clinical Studies and Medical Case Reports*. <https://doi.org/10.46998/ijcmcr.2023.34.00842>.
- Salazar, D., Arancibia, M., Casado, S., Viteri, A., López-Caballero, M., & Montero, M. (2021). Green Banana (*Musa acuminata* AAA) Wastes to Develop an Edible Film for Food Applications. *Polymers*, 13. <https://doi.org/10.3390/polym13183183>.
- Santhoskumar, A., Vaishnavi, R., Karunakaran, T., & Chitra, N. (2019). Studies on Mechanical Properties and Biodegradation of Edible Food Wrapper from Banana Peel. 07,1-4. <https://doi.org/10.33980/ajabs.2019.v07i02.001>.
- Shen, M., Song, B., Zeng, G., Zhang, Y., Huang, W., Wen, X., & Tang, W. (2020). Are biodegradable plastics a promising solution to solve the global plastic pollution?. *Environmental Pollution*, 263, 114469. <http://dx.doi.org/10.1016/j.envpol.2020.114469>
- Silva, V., Macedo, M., Rodrigues, C., Santos, A., Loyola, A., & Fante, C. (2020). Biodegradable edible films of ripe banana peel and starch enriched with extract of *Eriobotrya japonica* Leaves. *Food bioscience*, 38, 100750. <https://doi.org/10.1016/j.fbio.2020.100750>.
- Subagio, A., Morita, N., & Sawada, S. (1996). Carotenoids and their fatty-acid esters in banana peel. *Journal of nutritional science and vitaminology*, 42 6, 553-66. <https://doi.org/10.3177/JNSV.42.553>.
- Sultan, N., & Johari, W. (2017). The development of banana peel/corn starch bioplastic film: a preliminary study. *Bioremediation Science and Technology Research*. <https://doi.org/10.54987/bstr.v5i1.352>.
- Tarique, J., Sapuan, S. M., & Khalina, A. (2021). Effect of glycerol plasticizer loading on the physical, mechanical, thermal, and barrier properties of arrowroot (*Maranta arundinacea*) starch biopolymers. *Scientific reports*, 11(1), 13900.
- Taweachat, C., Wongsooka, T., & Rawdkuen, S. (2021). Properties of banana (*Cavendish spp.*) starch film incorporated with banana peel extract and its application. *Molecules*, 26(5),1406.<https://doi.org/10.3390/molecules26051406>
- Tugon, T. D. A., Larasati, R. D., Adnan, S., Sucimilawati, E., Agustiani, F. S., & Jaswir, I. (2023). Characterization of Banana Peel Pectin (*Musa acuminata Colla*) as a Potential Halal Pharmaceutical Excipient. *Indonesian Journal of Halal Research*, 5(1), 41-52.

- UNESCO. Plastic pollution in the ocean. Ocean Literacy Portal. <https://oceanliteracy.unesco.org/plastic-pollution-ocean/>
- Verma, P., Rani, R., Das, D., Rai, K. K., Gogoi, P., & Badwaik, L. S. (2024). Transformation of banana peel into biodegradable film added with starch and carboxymethyl cellulose and its characterization. *Sustainable Chemistry and Pharmacy*, 37, 101356. <https://doi.org/10.1016/j.scp.2023.101356>
- Vimal, Priya, S., Sathiya, Sheela, D., Shanthi, priya, E., Amitha, T.V., Aleena, B., Eluvathingal. (2024). Bioplastic Synthesis and Characterization from Banana Peel. *International Journal of Research Publication and Reviews*, 5(4):7878-7883.
- Vonnie, J., Rovina, K., 'Aqilah, N., & Felicia, X. (2023). Development and Characterization of Biosorbent Film from Eggshell/Orange Waste Enriched with Banana Starch. *Polymers*, 15. <https://doi.org/10.3390/polym15112414>.
- Vu, H., Scarlett, C., & Vuong, Q. (2018). Phenolic compounds within banana peel and their potential uses: A review. *Journal of Functional Foods*, 40, 238-248. <https://doi.org/10.1016/J.JFF.2017.11.006>.
- Zaini, H. M., Roslan, J., Saallah, S., Munsu, E., Sulaiman, N. S., & Pindi, W. (2022). Banana peels as a bioactive ingredient and its potential application in the food industry. *Journal of Functional Foods*, 92, 105054.
- Zhang, W., Li, X., & Jiang, W. (2019). Development of antioxidant chitosan film with banana peels extract and its application as coating in maintaining the storage quality of apple. *International journal of biological macromolecules*. <https://doi.org/10.1016/j.ijbiomac.2019.10.275>.
- Zhang, W., Li, X., & Jiang, W. (2020). Development of antioxidant chitosan film with banana peels extract and its application as coating in maintaining the storage quality of apple. *International journal of biological macromolecules*, Zaini 154,1205-1214. <https://doi.org/10.1016/j.ijbiomac.2019.10.275>
- Zhang, X., Ni, H., Xu, X., Li, L., Kang, H., & Li, D. (2024). Recent Advancements in the Synthesis, Functionalization, and Utilization of Cellulose Nanocrystals. *Resources Chemicals and Materials*. <https://doi.org/10.1016/j.recmm.2024.05.003>
- Rajini, N., Alavudeen, A., Siengchin, S., Rajulu, V., & Ayrilmis, N. (2021). Development and analysis of completely biodegradable cellulose/banana peel powder composite films. *Journal of Natural Fibers*. <https://doi.org/10.1080/15440478.2019.1612811>
- Tak, J. K., & Jain, S. (2019). Development of banana edible film and assessment of physicochemical properties. *International Research Journal of Pure and Applied Chemistry*, 20(2), 1-6. <https://doi.org/10.9734/irjpac/2019/v20i230129>
- Azieyanti, N., Amirul, A., Othman, S., & Misran, H. (2020). Mechanical and Morphology Studies of Bioplastic-Based Banana Peels. *Journal of Physics: Conference Series*, 1529. <https://doi.org/10.1088/1742-6596/1529/3/032091>.
- Khamsucharit P, Laohaphatanalert K, Gavinlertvatana P, Siroth K, Sangseethong K. Characterization of pectin extracted from banana peels of different varieties. *Food Sci Biotechnol*. 2017 Dec 27;27(3):623-629. <http://doi.org/10.1007/s10068-017-0302-0>. PMID: 30263788; PMCID: PMC6049672.
- Groh, K., Backhaus, T., Carney-Almroth, B., Geueke, B., Inostroza, P., Lennquist, A., Leslie, H., Maffini, M., Slunge, D., Trasande, L., Warhurst, A., & Muncke, J. (2019). Overview of known plastic packaging-associated chemicals and their hazards. *The Science of the total environment*, 651 Pt 2, 3253-3268 . <https://doi.org/10.1016/j.scitotenv.2018.10.015>.
- Irzalinda, A., & Ardi, R. (2020). Environmental Impact Evaluation of Flexible Plastic Packaging using Life Cycle Assessment Approach. *Proceedings of the 3rd Asia Pacific Conference on Research in Industrial and Systems Engineering*. <https://doi.org/10.1145/3400934.3400971>.
- Muncke, J. (2021). Tackling the toxics in plastics packaging. *PLoS Biology*, 19. <https://doi.org/10.1371/journal.pbio.3000961>.
- Kadac-Czapska, K., Knez, E., Gierszewska, M., Olewnik-Kruszkowska, E., & Grembecka, M. (2023). Microplastics derived from food

packaging waste—Their origin and health risks. *Materials*, 16(2), 674.  
Devika, R., & Saha, R. (2024). Characterization

and optimization studies of cellulose based bioplastics extracted from *Musa paradisiaca L.*

**Disclaimer/Publisher's Note:** The statements, opinions and data contained in all publications are solely those of the individual author(s) and contributor(s) and not of the publisher and/or the editor(s). This publisher and/or the editor(s) disclaim responsibility for any injury to people or property resulting from any ideas, methods, instructions or products referred to in the content.

---

© Copyright (2024): Author(s). The licensee is the journal publisher. This is an Open Access article distributed under the terms of the Creative Commons Attribution License (<http://creativecommons.org/licenses/by/4.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

*Peer-review history:*

*The peer review history for this paper can be accessed here:*

<https://www.sdiarticle5.com/review-history/126344>